

## NBR 70-compound 36624 - Technical Data Sheet

### 1. Introduction

NBR 70-compound 36624 is a Nitrile compound with medium percentage of acrylonitrile. Standard compound with good compression set values for contact with hydraulic fluids.

### 2. Product Description

<i>Chemical Composition</i>	: Acrylonitrile / Butadiene Rubber
<i>Physical form</i>	: O-Rings / Mouldings
<i>Colour</i>	: Black
<i>Odour</i>	: None
<i>Storage stability *</i>	: ± 7 years

\* : Following DIN 7716 conditions

### 3. Physical Properties

<i>Test Method</i>	<i>Norm</i>	<i>Test Values</i>
Hardness	DIN 53519	70° ± 5° IRHD
Tensile Strength at break	DIN 53504	min 13 MPa
Elongation at break	DIN 53504	min 250%
Specific Weight	ASTM D 1817	1,25
<b>Compression Set</b>	DIN 53517	
25% compression - 22h/100°C on slab		max 12%
on O-Ring (3,53 mm)	ASTM 395 B	max 20%
<b>Heat Ageing 70h/100°C</b>	DIN 53508	
Hardness Change		max +6°
Volume Change		max -2,1%
<b>Immersion in ASTM oil n° 3</b>	DIN 53521	
Hardness Change		max -5°
Volume Change		max +9%
Weight Change		max +6%

### 4. Temperature Resistance

- -30° to +120°C
- TR10 (low temp. resistance): -16°C

### 5. Chemical Resistance

Alkali	: very good
Air	: excellent
Alcohol	: very good
Fats	: excellent
Mineral oils	: excellent
Silicone oils	: excellent
Vegetable oils	: excellent
Inorganic acids	: excellent
Ketones	: unsatisfactory
Ethers	: unsatisfactory
Organic acids	: fair
Inorganic acids	: excellent

### 6. Advantages

- Low compression set
- Stock item for ca 12.000 dimensions
- Standard O-Ring compound
- good balance price/lifetime

### 7. Other Information

- Can be formulated to meet FDA 177.2600 compliance

This information is, to the best of our knowledge, accurate and reliable to the date indicated. The above mentioned data have been obtained by tests we consider as reliable. We don't assure that the same results can be obtained in other laboratories, using different conditions by the preparation and evaluation of the samples.